

Technical Data Sheet



Vision Coated 620gsm Double Sided

Material	Coated Double Sided PVC			
Stock widths	320 cm / 500cm			
Weight				
acc. to DIN EN ISO 2286-2	620	[g/m ²]	+- 3	[%]
Transmittance	15.2			%
ASTM E 424 1971 6.5.2				
Tensile Strength Warp	2460			N/5cm
ISO 13934-1:1999				
Tensile Strength Weft	2199			N/5cm
ISO 13934-1:1999				
Tearing Strength Warp	172			N
ISO 13934-1:2000				
Tearing Strength Weft	124			N
ISO 13934-1:2000				
Elongation Weft	25.7			%
ISO 13934-1:1999				
Elongation Warp	30			%
ISO 13934-1:1999				
Adhesion Strength warp/weft	73/129			N/5cm
Colourfast to weathering	B1			grade

Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG
T: 01494 760240 E : sales@dpm.com W : www.dpm.com