

# Vision Soft Coated Satin



dpm

digital print media

## Technical Data Sheet

### Vision Soft Coated Satin

With INKTeX+BS® finishing for direct print, with flame retardant treatment, tested to EN13501.

Material 100 % Polyester

Stock widths app. 310 cm,

Finishing Rolled on paper cores

Ecology According to Öko-Tex Standard 100, product class IV

#### Weight

|                      |        |                     |       |     |
|----------------------|--------|---------------------|-------|-----|
| acc. to DIN EN 12127 | 125.00 | [g/m <sup>2</sup> ] | + - 3 | [%] |
|----------------------|--------|---------------------|-------|-----|

#### Shrinkage

Heat Shrinkage, 195 °C, 90 sec,  
lengthwise

|                  |       |     |       |     |
|------------------|-------|-----|-------|-----|
| acc. to AA 25-02 | -2.00 | [%] | + - 1 | [%] |
|------------------|-------|-----|-------|-----|

Heat Shrinkage, 195 °C, 90 sec,  
crosswise

|                  |       |     |       |     |
|------------------|-------|-----|-------|-----|
| acc. to AA 25-02 | -2.00 | [%] | + - 1 | [%] |
|------------------|-------|-----|-------|-----|

#### Tearing strength

Maximum tensile elongation, longitudinal  
direction

|                            |       |     |        |     |
|----------------------------|-------|-----|--------|-----|
| acc. to DIN EN ISO 13934-1 | 60.00 | [%] | + - 20 | [%] |
|----------------------------|-------|-----|--------|-----|

Maximum tensile elongation, cross direction

|                            |       |     |        |     |
|----------------------------|-------|-----|--------|-----|
| acc. to DIN EN ISO 13934-1 | 25.00 | [%] | + - 20 | [%] |
|----------------------------|-------|-----|--------|-----|

Maximum tearing strength, longitudinal  
direction

|                            |             |          |
|----------------------------|-------------|----------|
| acc. to DIN EN ISO 13934-1 | min. 125.00 | [N/5 cm] |
|----------------------------|-------------|----------|

Maximum tearing strength, cross direction

|                            |              |          |
|----------------------------|--------------|----------|
| acc. to DIN EN ISO 13934-1 | min. 1000.00 | [N/5 cm] |
|----------------------------|--------------|----------|



Roseash Limited , Unit B, The Heights Business Park, Ibstone Road, Stokenchurch, HP14 3BG

T : 01494 760240

E : sales@dpm.com

W : www.dpm.com